FINAL REPORT

CERTIFICATE No.: 25947



Boral Cement Limited
ABN 62 008 528 523
Taylor Avenue New Berrima NSW 2577
Locked Bag 4 New Berrima NSW 2577
T +61 2 4860 2222

TEST CERTIFICATE OF: Geelong Daily Despatch Environment

PRODUCED AT: Boral Cement Limited Geelong

TESTED AT: Berrima Works Laboratory

SAMPLE IDENTIFICATION: GDDNM2401726

DATE DESPATCHED: 3/26/2024

PROPERTY	REQUIREMENTS OF AS 3582.2	RESULT
Insoluble Residue (AS 3583.14)		0.0 %
LOI (AS 3583.3)		-0.1 %
SO ₃ (AS 2350.2; TM 10.01.07)		2.8 %
MgO (AS 2350.2)	≤ 15.0 %	5.1 %
Al ₂ O ₃ (AS 2350.2)	≤ 18.0 %	13.8 %
Fe ₂ O ₃ (AS 2350.2) expressed as FeO *		0.6 % 0.5 %
Mn ₂ O ₃ (AS 2350.2) expressed as MnO *		0.2 % 0.2 %
Total Alkali (AS 2350.2)		0.4 %
CI (AS 2350.2)	≤ 0.1 %	0.01 %
Fineness passing 45µm sieve (AS 3583.1)		98 %
Fineness Index (AS/NZ 2350.8)		$445 \text{ m}^2/\text{kg}$

REMARKS

Sampling not carried out by laboratory. Samples tested as received and results only relate to the item tested.

NATA

Jason Nairn National Technical Manager

Accredited for compliance with ISO/IEC 17025 - Testing

NATA Accreditation Number: 530 / 531 Page 1 of 1 Date of Issue: 5/30/2024

^{*} NATA accreditation does not cover the performance of this service.



Page 1 of 1 Report Template - Rev. (3) Jul 2021 Authorised by M. A.

Boral Construction Materials

Materials Technical Services

Unit 4, 3–5 Gibbon Road, Baulkham Hills NSW 2153 Australia PO Box 400, Winston Hills NSW 2153

> T +61 (02) 9624 9900 boral.com.au

TEST REPORT - MILLED SLAG

CLIENT:

BORAL CEMENT - (TECHNICAL)

FILE NO: 50/24

ADDRESS:

39 Delhi Road, North Ryde, NSW 2113

REQUEST NO: 111982

LAB SAMPLE NO: 302097

SOURCE OF SAMPLE: Boral Cement - Geelong

DATE RECEIVED: 29/04/2024

SAMPLE IDENTIFICATION: Environment ID # GDDNM2401726 - Date sampled: 26/03/2024

IDENTIFICATION OF CEMENT USED: Boral Cement SL Berrima Ref. 2019

TEST METHOD: AS 3583: Methods of test for supplementary cementitious materials for use with Portland

cement

PROPERTY	TEST METHOD	RESULT	DATE TESTED
Relative density Relative water requirement Relative strength 7 days (accelerated) Relative strength 28 days (standard)	AS 3583.5	2.88	01/05/2024
	AS 3583.6	103%	02/05/2024
	AS 3583.6	93%	09/05/2024
	AS 3583.6	90%	30/05/2024

Melody mancenido, Parisa Sowti, Violeta Paicu, Jason Nairn, Mat File, File

Note:

Sample supplied by the client and tested as received.

Approved signatory

Serial no.

Sam El-Hamawi

CEM111982.SE.1

