

FINAL REPORT

CERTIFICATE No.: 26566



Boral Cement Limited

ABN 62 008 528 523

Taylor Avenue New Berrima NSW 2577

Locked Bag 4 New Berrima NSW 2577

T +61 2 4860 2222

TEST CERTIFICATE OF: Geelong Daily Despatch Environment
PRODUCED AT: Boral Cement Limited Geelong
TESTED AT: Berrima Works Laboratory
SAMPLE IDENTIFICATION: GDDNM2405116
DATE DESPACHED: 29/10/2024

PROPERTY	REQUIREMENTS OF AS 3582.2	RESULT
Insoluble Residue (AS 3583.14)		0.1 %
LOI (AS 3583.3)		0.9 %
SO ₃ (AS 2350.2; TM 10.01.07)		2.7 %
MgO (AS 2350.2)	≤ 15.0 %	5.9 %
Al ₂ O ₃ (AS 2350.2)	≤ 18.0 %	13.7 %
Fe ₂ O ₃ (AS 2350.2) expressed as FeO *		0.5 % 0.4 %
Mn ₂ O ₃ (AS 2350.2) expressed as MnO *		0.2 % 0.2 %
Total Alkali (AS 2350.2)		0.5 %
Cl (AS 2350.2)	≤ 0.1 %	< 0.01 %
Fineness passing 45µm sieve (AS 3583.1)		98 %
Fineness Index (AS/NZ 2350.8)		490 m ² /kg

REMARKS

Sampling not carried out by laboratory. Samples tested as received and results only relate to the item tested.

* NATA accreditation does not cover the performance of this service.

A handwritten signature in blue ink, appearing to read "S. N. A. R. A.", with a horizontal line underneath.



Building something great

TEST REPORT – MILLED SLAG

CLIENT: BORAL CEMENT – (TECHNICAL)

FILE NO: 50/24

ADDRESS: 39 Delhi Road, North Ryde, NSW 2113

REQUEST NO: 115486

LAB SAMPLE NO: 312592

SOURCE OF SAMPLE: Boral Cement - Geelong

DATE RECEIVED: 31/10/2024

SAMPLE IDENTIFICATION: Enviroment ID # GDDNM2405116 - Date sampled: 29/10/2024

IDENTIFICATION OF CEMENT USED: Boral Cement SL Berrima Ref. 2022

TEST METHOD: AS 3583: Methods of test for supplementary cementitious materials for use with Portland cement

PROPERTY	TEST METHOD	RESULT	DATE TESTED
Relative density	AS 3583.5	2.85	20/11/2024
Relative water requirement	AS 3583.6	103%	21/11/2024
Relative strength 7 days (accelerated)	AS 3583.6	103%	28/11/2024
Relative strength 28 days (standard)	AS 3583.6	100%	19/12/2024

Melody mancenido, Violeta Paicu, Jason Nairn, Mat File, File

Note:

- Sample supplied by the client and tested as received.

Approved signatory

Sam El-Hamawi

CEM115486.SE.1

Date

19/12/2024

Serial no.





**Building
something
great**

TEST REPORT

CLIENT: BORAL CEMENT – TECHNICAL
39 Delhi Road, North Ryde, NSW 2113.

FILE No.:50/24

PROJECT: Testing of Enviroment Sample from Boral Cement – Geelong.

REQUEST No.: 115486

TEST PROCEDURE:

AS 3583.12 – 1991 – Determination of Available Alkali

Laboratory Sample No.: 312592
Date Sampled: 29/10/2024
Date Received: 31/10/2024
Date Tested: 10/12/2024
Sample Description: Enviroment ID #
GDDNM2405116
Field No.: 1

TEST RESULTS:

Sodium as Na₂O (m/m %) 0.04
Potassium as K₂O (m/m %) 0.07
Available Alkali (m/m %) 0.1

Available Alkali (m/m %) = Na₂O (%) + (0.658 x K₂O %)

Note:

- Sample was provided by the Client and tested as received.

Violeta Paicu, Melody Mancenido, Jason Nairn, Mat.File, File.

Approved signatory

Nanthini Selvadurai

Date 11-12-24

Serial no. CHEM115486.NS.1



NATA Accredited Laboratory
Number: 9968



**Building
something
great**

TEST REPORT

CLIENT: BORAL CEMENT – TECHNICAL
39 Delhi Road, North Ryde, NSW 2113.

FILE No.:50 / 24

PROJECT: Testing of Enviroment Sample from Boral Cement – Geelong.

REQUEST No.: 115486

TEST PROCEDURE: AS 3583.7 – Determination of Sulfide Sulfur content

Laboratory Sample No.: 312592
Date Sampled: 29/10/2024
Date Received: 31/10/2024
Date Tested: 26/11/2024
Sample Description: Enviroment ID #
GDDNM2405116
Field No.: 1

TEST RESULTS:

Sulfide Sulfur as S (%) 0.28

Sample submitted by the Client.

- Sample was provided by the Client.
- Test results in this test report relate only to the sample tested.
- This report shall not be reproduced except in full without the approval of the Boral MTS Laboratory.

Nanthini S

11th December 2024.

Violeta Paicu, Melody Mancenido, Jason Nairn, Mat.File, File.