

FINAL REPORT

CERTIFICATE No.: 25700



Boral Cement Limited

N 62 008 528 523

Taylor Avenue New Berrima NSW 2577

Locked Bag 4 New Berrima NSW 2577

T +61 2 4860 2222

TEST CERTIFICATE OF: Marulan Quicklime Fines - Despatch Composite
PRODUCED AT: Boral Cement Limited Marulan
TESTED AT: Berrima Works Laboratory
SAMPLE IDENTIFICATION: LDQLF2400328
DATE SAMPLED: for date ending 24/01/2024

PROPERTY	RESULT
Chemical Composition (AS 4489.5.1)	
CaO	91.4 %
MgO	0.9 %
Al ₂ O ₃	0.5 %
SiO ₂	1.2 %
K ₂ O	0.1 %
Fe ₂ O ₃	0.4 %
LOI (AS 4489.7.1)	4.8 %
ALI as CaO (AS 4489.6.1)	86.3 %
Slaking (AS 4489.3.1)	
Temperature Rise at 30 s	33.0 °C
Temperature Rise at 3 min	43.5 °C
Total Temperature Rise	44.0 °C
Total Active Slaking Time	3.3 mins
Residue on Slaking	0.96 %
Particle Size Distribution * (AS 1141.11.1)	
< 4.75 mm	100 %
< 2.36 mm	100 %
< 1.18 mm	99 %
< 600 µm	94 %

REMARKS

Sampling not carried out by laboratory. Samples tested as received.

* Samples are not washed.



Accredited for compliance with ISO/IEC 17025 - Testing

Marc Smith
Technical Services Manager