

FINAL REPORT

CERTIFICATE No.: 27178



Boral Cement Limited
ABN 62 008 528 523
Taylor Avenue New Berrima NSW 2577
Locked Bag 4 New Berrima NSW 2577
T +61 2 4860 2222

TEST CERTIFICATE OF: Maldon Daily Despatch General Purpose Bagged Cement
PRODUCED AT: Boral Cement Limited Maldon
TESTED AT: Berrima Works Laboratory
SAMPLE IDENTIFICATION: MBGGP2501884
DATE DESPATCHED: 26/05/2025

PROPERTY	REQUIREMENTS OF AS 3972		RESULT
Compressive Strength (AS/NZS 2350.11)			
3 Day			34.8 MPa
7 Day	Minimum	35 MPa	49.0 MPa
28 Day	Minimum	45 MPa	63.8 MPa
Setting Time (AS/NZS 2350.4)			
Initial	Minimum	45 mins	135 mins
Final	Maximum	360 mins	165 mins
Soundness (AS/NZS 2350.5)	Maximum	5 mm	0 mm
SO ₃ (AS 2350.2)	Maximum	3.5 %	2.7 %
Cl (AS 2350.2)	Maximum	0.10 %	0.02 %

OTHER REPORTABLE PROPERTIES

CHEMICAL

K₂O (AS 2350.2) 0.56 %
Na₂O (AS 2350.2) 0.10 %
LOI (AS 2350.2) 2.7 %

PHYSICAL

Normal Consistency (AS/NZS 2350.3) 26.8 %
Fineness Index (AS/NZS 2350.8) 350 m²/kg

REMARKS

Preparation of mortar and moulding of specimens in accordance with AS 2350.12.
Sampling not carried out by laboratory. Samples tested as received and results only relate to the item tested.
This cement is a Type GP cement with up to 7.5% mineral addition.



Accredited for compliance with ISO/IEC 17025 - Testing

NATA Accreditation Number: 530 / 531

Page 1 of 1

Melody Mancenido
Technical Services Manager
Date of Issue: 8/8/2025