

FINAL REPORT

CERTIFICATE No.: 25765



Boral Cement Limited

ABN 62 008 528 523

Taylor Avenue New Berrima NSW 2577

Locked Bag 4 New Berrima NSW 2577

T +61 2 4860 2222

TEST CERTIFICATE OF: Maldon Daily Despatch Builders Cement
PRODUCED AT: Boral Cement Limited Maldon
TESTED AT: Berrima Works Laboratory
SAMPLE IDENTIFICATION: MDDBU2400615
DATE DESPATCHED: 2/20/2024

PROPERTY	REQUIREMENTS OF AS 3972		RESULT
Compressive Strength (AS/NZS 2350.11)			
3 Day			22.6 MPa
7 Day	Minimum	20 MPa	34.8 MPa
28 Day	Minimum	35 MPa	55.8 MPa
Setting Time (AS/NZS 2350.4)			
Initial	Minimum	45 mins	195 mins
Final	Maximum	600 mins	270 mins
Soundness (AS/NZS 2350.5)	Maximum	5 mm	1 mm
SO ₃ (TM 10.01.07)	Maximum	3.5 %	2.1 %
CI (AS 2350.2)	Maximum	0.10 %	0.01 %

OTHER REPORTABLE PROPERTIES

CHEMICAL

PHYSICAL

Normal Consistency (AS/NZS 2350.3)	28.3 %
Fineness Index (AS/NZS 2350.8)	360 m ² /kg

REMARKS

Preparation of mortar and moulding of specimens in accordance with AS 2350.12.

Sampling not carried out by laboratory. Samples tested as received and results only relate to the item tested.

This cement is a Type GB cement with nominally 35% slag.

A blue ink handwritten signature, appearing to be "J. W.", is located in the bottom right corner of the page.