

Boral CE2

SPECIALITIES

2018 EDITION

Product Description

- Boral CE2 is a clay thickened, bitumen emulsion.
- Designed as a protective membrane over insulation in cool rooms.
- Trowelable consistency.
- Based on stable ASS bitumen emulsions meeting AS1006.
- Stable in storage and reduces the potential for bleeding in service.
- Available in 20 litre and 205 litre drums.
- CE2 is water resistant, but not designed for waterproofing (ie. consistent immersion in water).

Safety Information

A Material Safety Data Sheet for Boral CE2 is available upon request by contacting Boral Asphalt customer service.



Preparation

- Surfaces to be coated should be clean and free from dust and oils.
- CE2 can be thinned (diluted), if necessary with clean, potable water.
- Stir back in any liquid that has separated and is sitting on top of the emulsion in the drum.
- Protect the drum from frost, as the product will break and be unusable if frozen.
- Clean up tools while still wet with clean water.
- If material has set, it may be cleaned off tools with mineral turpentine.

Application

- Generally, the application rate is approximately 2 litres/m². Application rates may vary according to site conditions.
- CE2 should be applied with a trowel in layers maximum 3mm thick. Shrinkage cracking may occur with thicker layers.
- Drying time between coats is generally between 8-16 hours.
- CE2 will give a black finish initially, but the surface will oxidise in sunlight over time.

Boral website:

Visit the Boral website for the full range of Boral products: www.boral.com.au

Asphalt information:

For asphalt news and information visit: www.boral.com.au/asphalt

For asphalt locations around Australia go to: www.boral.com.au/locations

Contact us:

At Boral we are committed to excellence in service so for further information please contact:

NSW (02) 8801 2000
VIC 1300 132 964
QLD (07) 3268 8011
SA (08) 8425 0400
WA (08) 9458 0400

or visit: www.boral.com.au/contact