FINAL REPORT

CERTIFICATE No.: 25328



Boral Cement Limited N 62 008 528 523 Taylor Avenue New Berrima NSW 2577 Locked Bag 4 New Berrima NSW 2577 T +61 2 4860 2222

TEST CERTIFICATE OF: Tarong Daily Despatch Grade 1 Fly Ash

PRODUCED AT: Boral Cement Limited Tarong

TESTED AT: Berrima Works Laboratory

SAMPLE IDENTIFICATION: TDDFA2304037

DATE DESPATCHED: 21/09/2023

PROPERTY	REQUIREM	MENTS OF AS 3582.1 - Grade 1	RESULT
Fineness (AS 3583.1)	≥	75 %	91 %
LOI (AS 3583.3)	≤	4.0 %	1.7 %
Moisture (AS 3583.2)	≤	0.5 %	< 0.1 %
SO ₃ (AS 2350.2)	≤	3.0 %	< 0.1 %
SiO ₂ (AS 2350.2)			74.0 %
Al ₂ O ₃ (AS 2350.2)			20.9 %
Fe ₂ O ₃ (AS 2350.2)			1.4 %
Chemical Composition (AS 2350.2)	≥	70 %	96 %
Total Alkali (AS 2350.2)			0.3 %
CI (AS 2350.2)	≤	0.1 %	0.02 %

REMARKS

Sampling not carried out by laboratory. Samples tested as received.

NATA

Accredited for compliance with ISO/IEC 17025 - Testing

Marc Smith
Technical Services Manager

NATA Accreditation Number: 530 / 531 Page 1 of 1 Date of Issue: 3/11/2023



Boral Construction Materials Materials Technical Services

Unit 4, 3–5 Gibbon Road Baulkham Hills NSW 2153 Australia

PO Box 400, Winston Hills NSW 2153

T +61 (02) 9624 9900

boral.com.au

TEST REPORT - FLYASH

CLIENT: BORAL CEMENT – (TECHNICAL)

FILE NO: 50/23

ADDRESS: 39 Delhi Road, North Ryde, NSW 2113

REQUEST NO: 108270

SAMPLE IDENTIFICATION: TDDFA2304037

LAB SAMPLE NO: 2

291787

SOURCE OF SAMPLE:

Boral Cement - Berrima

DATE SAMPLED:

21/09/2023

DATE RECEIVED:

03/10/2023

IDENTIFICATION OF CEMENT USED: Boral Cement SL Berrima Ref. 2022

TEST METHOD: AS 3583: Methods of test for supplementary cementitious materials for use with Portland cement

PROPERTY	DATE TESTED	RESULT	TEST METHOD	
Relative density	11/10/2023	2.13	AS 3583.5	
Relative water requirement	12/10/2023	103%	AS 3583.6	
Relative strength 7 days (accelerated)	19/10/2023	97%	AS 3583.6	

Note:

• Sample supplied by the client and tested as received.

Marc Smith, Parisa Sowti, Violeta Paicu, Mat. File, File

Approved Signatory

Date 2

Sam El-Hamawi

Serial No.

CEM108270.SE,2

IAC MRA

