

FINAL REPORT

CERTIFICATE No.: 25397



Boral Cement Limited

N 62 008 528 523

Taylor Avenue New Berrima NSW 2577

Locked Bag 4 New Berrima NSW 2577

T +61 2 4860 2222

TEST CERTIFICATE OF: Tarong Daily Despatch Grade 1 Fly Ash
PRODUCED AT: Boral Cement Limited Tarong
TESTED AT: Berrima Works Laboratory
SAMPLE IDENTIFICATION: TDDFA2304393
DATE DESPATCHED: 11/10/2023

PROPERTY	REQUIREMENTS OF AS 3582.1 - Grade 1	RESULT
Fineness (AS 3583.1)	≥ 75 %	87 %
LOI (AS 3583.3)	≤ 4.0 %	2.1 %
Moisture (AS 3583.2)	≤ 0.5 %	0.2 %
SO ₃ (AS 2350.2)	≤ 3.0 %	< 0.1 %
SiO ₂ (AS 2350.2)		71.9 %
Al ₂ O ₃ (AS 2350.2)		22.1 %
Fe ₂ O ₃ (AS 2350.2)		1.4 %
Chemical Composition (AS 2350.2)	≥ 70 %	95 %
Total Alkali (AS 2350.2)		0.3 %
Cl (AS 2350.2)	≤ 0.1 %	< 0.01 %

REMARKS

Sampling not carried out by laboratory. Samples tested as received.



Accredited for compliance with ISO/IEC 17025 - Testing

A handwritten signature in blue ink, appearing to read "Marc Smith".

Marc Smith
Technical Services Manager

**Boral Construction Materials
Materials Technical Services**Unit 4, 3-5 Gibbon Road
Baulkham Hills NSW 2153 Australia

PO Box 400, Winston Hills NSW 2153

T +61 (02) 9624 9900

boral.com.au**TEST REPORT – FLYASH**

CLIENT: BORAL CEMENT – (TECHNICAL)

FILE NO: 50/23

ADDRESS: 39 Delhi Road, North Ryde, NSW 2113

REQUEST NO: 108781

SAMPLE IDENTIFICATION: TDDFA2304393

LAB SAMPLE NO: 293246

SOURCE OF SAMPLE: Boral Cement - Berrima

DATE SAMPLED: 11/10/2023

DATE RECEIVED: 31/10/2023

IDENTIFICATION OF CEMENT USED: Boral Cement SL Berrima Ref. 2022

TEST METHOD: AS 3583: Methods of test for supplementary cementitious materials for use with Portland cement

PROPERTY	DATE TESTED	RESULT	TEST METHOD
Relative density	01/11/2023	2.10	AS 3583.5
Relative water requirement	02/11/2023	102%	AS 3583.6
Relative strength 7 days (accelerated)	09/11/2023	96%	AS 3583.6

Note:

- Sample supplied by the client and tested as received.

Marc Smith, Parisa Sowti, Violeta Paicu, Mat. File, File

Approved Signatory

Sam El-Hamawi

Date

20/11/23

Serial No.

CEM108781.SE.1

